



**DIVERSIFIED**  
TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

November 13, 2024

Ms. Martha Boynton  
DESIGN CRAFT FABRIC CORPORATION  
2230 Ridge Drive  
Glenview, IL 60025

Reference: Laboratory Test Report  
Lab Identification No. 62173  
Invoice No. 93489

Dear Ms. Boynton:

One (1) sample, identified as **STYLE: BROAD STROKES, COLOR: S403**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2023 Edition, (Test 1)". ***Per your request, the sample was tested after five (5) commercial laundering cycles at 160F (Tumble Dry).*** The results are as follows:

<u>Test Results</u>		
<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	11.35
2	0.0	10.89
3	0.0	7.98
4	0.0	15.66
5	0.0	17.41
6	0.0	13.62
7	0.0	14.11
8	0.0	9.47
9	0.0	12.38
<u>10</u>	<u>0.0</u>	<u>14.33</u>
<b>AVG</b>	<b>0.0</b>	<b>12.72</b>

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

Sincerely,

Brian S. Dement

BSD/mr

