

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

September 12, 2024

Ms. Martha Boynton
DESIGN CRAFT FABRIC CORPORATION
2230 Ridge Drive
Glenview, IL 60025

Reference: Laboratory Test Report
Lab Identification No. 61346
Invoice No. 92676

Dear Ms. Boynton:

One (1) sample, identified as **STYLE: HOME COURT, COLOR: S396**, was received and tested in accordance with CAN/ULC-S109-14, "Standard for Flame Tests of Flame-Resistant Fabrics and Films", Small-Flame Test. The results are as follows:

Test Results

<u>Specimen Number</u>	<u>Residual Flame (sec)</u>		<u>Damaged Length (mm)</u>	
	<u>Warp</u>	<u>Fill</u>	<u>Warp</u>	<u>Fill</u>
1	0.0	0.0	94	98
2	0.0	0.0	104	111
3	0.0	0.0	118	120
4	0.0	0.0	103	132
5	0.0	0.0	107	103
Avg.			109	


The fabric sample submitted **meets** the minimum requirements of the Small-Flame Test. The maximum average damaged length shall not exceed 165 millimeters and the maximum damaged length for any individual specimen shall not exceed 190 millimeters. No residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

September 12, 2024

Ms. Martha Boynton
DESIGN CRAFT FABRIC CORPORATION
2230 Ridge Drive
Glenview, IL 60025

Reference: Laboratory Test Report
Lab Identification No. 61346
Invoice No. 92676

Dear Ms. Boynton:

One (1) sample, identified as **STYLE: HOME COURT, COLOR: S396**, was received and tested in accordance with CAN/ULC-S109-14, "Standard for Flame Tests of Flame-Resistant Fabrics and Films", Large-Flame Test. The results are as follows:

Test Results

<u>Specimen Number</u>		<u>Residual Flame (sec)</u>	<u>Damaged Length (mm)</u>
Length	1	0.0	60
Length	2	0.0	59
Width	1	0.0	69
Width	2	0.0	99

The fabric sample submitted **meets** the minimum requirements of the Large-Flame Test. The length of char on the individual folded specimens shall not exceed 635 millimeters. No residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

Sincerely,

Brian S. Dement

BSD/mr

