



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

September 12, 2024

Ms. Martha Boynton
DESIGN CRAFT FABRIC CORPORATION
2230 Ridge Drive
Glenview, IL 60025

Reference: Laboratory Test Report
Lab Identification No. 61346
Invoice No. 92676

Dear Ms. Boynton:

One (1) sample, identified as **STYLE: HOME COURT, COLOR: S396**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2023 Edition, (Test 1)". ***Per your request, the sample was tested after five (5) commercial laundering cycles at 160F (Tumble Dry).*** The results are as follows:

Test Results

<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	7.05
2	0.0	8.10
3	0.0	10.18
4	0.0	10.19
5	0.0	10.12
6	0.0	8.70
7	0.0	12.08
8	0.0	7.84
9	0.0	4.09
<u>10</u>	<u>0.0</u>	<u>5.91</u>
AVG	0.0	8.43

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

Sincerely,

Brian S. Dement

BSD/mr

