



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

August 27, 2026

Ms. Martha Boynton
DESIGN CRAFT FABRIC CORPORATION
2230 Ridge Drive
Glenview, IL 60025

Reference: Laboratory Test Report
Lab Identification No. 69321
Invoice No. 100618

Dear Ms. Boynton:

One (1) sample, identified as **STYLE: PICKUPSTIX, COLOR: S429**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2023 Edition, (Test 1)". ***Per your request, the sample was tested after five (5) commercial laundering cycles at 160F (Tumble Dry).*** The results are as follows:

<u>Test Results</u>		
<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	13.89
2	0.0	22.19
3	0.0	17.31
4	0.0	17.17
5	0.0	17.39
6	0.0	11.06
7	0.0	20.62
8	0.0	16.50
9	0.0	13.58
<u>10</u>	<u>0.0</u>	<u>18.43</u>
AVG	0.0	16.82

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

Sincerely,

Brian S. Dement

BSD/mr

