



DIVERSIFIED
TESTING LABORATORIES, INC.
 WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
 P.O. BOX 4004
 BURLINGTON, NORTH CAROLINA 27215
 PHONE (336) 227-7710 • FAX (336) 227-1175
 www.diversifiedtestinglabs.com

September 29, 2020

Ms. Martha Boynton
 DESIGN CRAFT FABRIC CORPORATION
 2230 Ridge Drive
 Glenview, IL 60025

Reference: Laboratory Test Report
 Lab Identification No. 42809
 Invoice No. 74079

Dear Ms. Boynton:

One (1) fabric sample, identified as **STYLE: PICKUPSTIX, COLOR: S274**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2019 Edition, (Test 1)". **Per your request, the sample was tested after five (5) commercial laundering cycles at 160F (Tumble Dry).** The results are as follows:

Test Results

<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	14.74
2	0.0	13.84
3	0.0	9.47
4	0.0	15.64
5	0.0	13.29
6	0.0	16.17
7	0.0	13.17
8	0.0	16.20
9	0.0	8.09
<u>10</u>	<u>0.0</u>	<u>19.04</u>
AVG	0.0	13.97

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

