"We Test Per Your Request"——



September 15, 2025

Ms. Martha Boynton
DESIGN CRAFT FABRIC CORPORATION
2230 Ridge Drive
Glenview, IL 60025

Reference: Laboratory Test Report

Lab Identification No. 65571

Invoice No. 96879

Dear Ms. Boynton:

One (1) sample, identified as **STYLE: SHOWER SHIELD, COLOR: S415,** was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2023 Edition, (Test 1)". The results are as follows:

Test Results

Specimen Number	Residual Flame	Weight Loss
	(seconds)	(percent)
1	0.0	25.82
2	0.0	25.51
3	0.0	23.95
4	0.0	25.43
5	0.0	26.79
6	0.0	25.51
7	0.0	22.90
8	0.0	25.12
9	0.0	28.71
<u>10</u>	<u>0.0</u>	<u>23.04</u>
AVG	0.0	25.28

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

Sincerely,

Brian S. Dement

BSD/mr

