

"We Test Per Your Request"=

minimini,

WINNIN WIN

336 WEST FRONT STREET P.O. BOX 4004 BURLINGTON, NORTH CAROLINA 27215 PHONE (336) 227-7710 • FAX (336) 227-1175 www.diversifiedtestinglabs.com

July 13, 2020

Ms. Martha Boynton DESIGN CRAFT FABRIC CORPORATION 2230 Ridge Drive Glenview, IL 60025

Reference: Laboratory Test Report

Lab Identification No. 41869

Invoice No. 73095

Dear Ms. Boynton:

One (1) fabric sample, identified as STYLE: SQUARE ONE, COLOR: S266, was received and tested in accordance with CAN/ULC-S109-14, "Standard for Flame Tests of Flame-Resistant Fabrics and Films", Small-Flame Test. The results are as follows:

<u>Test Results</u>					
Specimen Number	Residual Flame (sec)		Damaged Length (mm)		
	<u>Warp</u>	<u>Fill</u>	<u>Warp</u>	<u>Fill</u>	
1	0.0	0.0	104	97	
2	0.0	0.0	87	94	
3	0.0	0.0	137	117	
4	0.0	0.0	104	97	
5	0.0	0.0	124	104	
Avg.			107		

The fabric sample submitted **meets** the minimum requirements of the Small-Flame Test. The maximum average damaged length shall not exceed 165 millimeters and the maximum damaged length for any individual specimen shall not exceed 190 millimeters. No residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

WORLDWIDE SERVICE

-"We Test Per Your Request"——



July 13, 2020

Ms. Martha Boynton
DESIGN CRAFT FABRIC CORPORATION
2230 Ridge Drive
Glenview, IL 60025

Reference: Laboratory Test Report

Lab Identification No. 41869

Invoice No. 73095

Dear Ms. Boynton:

One (1) fabric sample, identified as **STYLE**: **SQUARE ONE**, **COLOR**: **S266**, was received and tested in accordance with CAN/ULC-S109-14, "Standard for Flame Tests of Flame-Resistant Fabrics and Films", Large-Flame Test. The results are as follows:

## **Test Results**

Specimen Number	Residual Flame (Seconds)	Char Length (Millimeters)
Length 1	0.0	38
Length 2	0.0	89
Width 1	0.0	114
Width 2	0.0	89

The fabric sample submitted **meets** the minimum requirements of the Large-Flame Test. The length of char on the individual folded specimens shall not exceed 635 millimeters. No residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr