



**DIVERSIFIED**  
TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
[www.diversifiedtestinglabs.com](http://www.diversifiedtestinglabs.com)

March 20, 2024

Ms. Martha Boynton  
DESIGN CRAFT FABRIC CORPORATION  
2230 Ridge Drive  
Glenview, IL 60025

Reference: Laboratory Test Report  
Lab Identification No. 58992  
Invoice No. 90314

Dear Ms. Boynton:

One (1) sample, identified as **STYLE: SHOWER MIST, COLOR: S384**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2023 Edition, (Test 1)". The results are as follows:

<u>Test Results</u>		
<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	19.07
2	0.0	31.35
3	0.0	23.72
4	0.0	26.16
5	0.0	23.30
6	0.0	22.33
7	0.0	17.34
8	0.0	20.78
9	0.0	19.79
<u>10</u>	<u>0.0</u>	<u>25.44</u>
<b>AVG</b>	<b>0.0</b>	<b>22.89</b>

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

Sincerely,

Brian S. Dement

BSD/mr

