



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

June 11, 2024

Ms. Martha Boynton
DESIGN CRAFT FABRIC CORPORATION
2230 Ridge Drive
Glenview, IL 60025

Reference: Laboratory Test Report
Lab Identification No. 60104
Invoice No. 91397

Dear Ms. Boynton:

One (1) sample, identified as **STYLE: SHOWER SHIELD, COLOR: S389**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2023 Edition, (Test 1)". The results are as follows:

Test Results

<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	8.38
2	0.0	11.99
3	0.0	6.46
4	0.0	21.66
5	0.0	6.04
6	0.0	19.89
7	0.0	10.06
8	0.0	18.93
9	0.0	18.95
<u>10</u>	<u>0.0</u>	<u>21.95</u>
AVG	0.0	14.43

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

Sincerely,

Brian S. Dement

BSD/mr

