



**DIVERSIFIED**  
**TESTING LABORATORIES, INC.**  
 WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET  
 P.O. BOX 4004  
 BURLINGTON, NORTH CAROLINA 27215  
 PHONE (336) 227-7710 • FAX (336) 227-1175  
 www.diversifiedtestinglabs.com

January 15, 2026

Ms. Martha Boynton  
 DESIGN CRAFT FABRIC CORPORATION  
 2230 Ridge Drive  
 Glenview, IL 60025

Reference: Laboratory Test Report  
 Lab Identification No. 66806  
 Invoice No. 98080

Dear Ms. Boynton:

One (1) sample, identified as **STYLE: TAKE NOTICE, COLOR: S419**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2023 Edition, (Test 1)". **Per your request, the sample was tested after five (5) commercial laundering cycles at 160F (Tumble Dry).** The results are as follows:

<b>Test Results</b>		
<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	4.01
2	0.0	4.32
3	0.0	6.24
4	0.0	1.94
5	0.0	3.95
6	0.0	0.30
7	0.0	14.30
8	0.0	2.00
9	0.0	9.06
<u>10</u>	<u>0.0</u>	<u>13.94</u>
<b>AVG</b>	<b>0.0</b>	<b>6.00</b>

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

Sincerely,

Brian S. Dement

BSD/mr

